

# Vapor Liquid Solid Growths of Germanium and Gallium Antimonide Nanowires

NSF

Rafael Alvarez<sup>1</sup>, Esmeralda Arreola<sup>2</sup>, Michael Oye<sup>3,</sup> Meyya Meyyappan<sup>3</sup>


<sup>1</sup> California State University Long Beach, <sup>2</sup> Utah State University, <sup>3</sup> NASA Ames Research Center

### Abstract

Determining the optimal growth parameters for germanium (Ge) and gallium antimonide (GaSb) nanowires is the focus of this research. Given that nano materials behave differently from their bulk counterparts we are researching several variables that influence nanowire diameter and length such as temperature, ramp rate, gas flow rate, and catalyst particle size.

## Background

- Nano materials can be engineered to make use of their optical properties.
- The infrared response (IR) of Ge and GaSb nanowires are directly controllable based on their geometry.



Fine tuning the IR response can lead to device integration for night vision and free space communications.


### Experimental


- A Vapor Liquid Solid (VLS) method was used along with adjustments to the following variables in order to observe their effect on nano growth:
- Gold (Au) colloidal catalyst. Batch sizes ranged from 2, 5, 10 and 50 nm.
- Catalyst spin coated at different rpm.
- Growth temperatures ranged from 820 900 °C.
- Growth time varied from 15 min to 1 hr.
- Argon gas flow varied from 50 to 100 sccm.


# Spin coat creates Au catalyst Insight toward experiment temp Tube Furnace Insight toward experiment temp Samples of silicon substrates placed at varying distances Ge or GaSb inside crucible


## **Growth Examples**


- Float and/or Root growth can occur during VLS.
- In both cases, the catalyst is active at the growth site.













# Analysis – SEM/EDS



- Scanning Electron Microscope/Energy Dispersive Spectrometer Elemental analysis.
- Analysis indicates presence of gallium oxide and germanium oxide, respectively.

## Results - Scanning Electron Microscope



- Top row: comparison of nanowire size differences.
- Bottom row: some oddities of nano growth.

### Conclusion

- The goal of this research involves synthesizing Ge and GaSb nanowires via the VLS method.
- Our initial attempts proved successful in growing germanium oxide and gallium oxide nanowires of varying lengths. Some nanowires are approximately 200  $\mu$ m in length.
- © Current uses for germanium oxide and gallium oxide nanowires include IR sensor technology.
- Further research to eliminate the source of oxygen so that pure Ge and GaSb nanowires can be grown is underway – this includes determining if the above-referenced experimental variables are the source.

### References and Acknowledgments

Kolasinski, K. (2007). *Catalytic growth of nanowires: Vapor-liquid-solid, Vapor-solid-solid, solution-liquid-solid and solid-liquid-solid growth*. Current Opinion in Solid State & Materials Science. 10 (3-4), pp 182-191.

Wang, Z. (2007) *Piezoelectric Nanostructures: From Growth Phenomena to Electric Nanogenerators*. MRS Bulletin. 32 (2), PP 109-116. Yiying Wu, Y., Yang, P. (2001). *Direct Observation of Vapor-Liquid-Solid Nanowire Growth*. JACS. 123 (13), PP 3165-3166.

We acknowledge the STAR program and the use of the UCSC MACS Facility at NASA Ames, established with the support of NASA grant NNX09AQ44A. This material is based upon work supported by the S.D. Bechtel, Jr. Foundation and by the National Science Foundation under Grant No. 0952013. Any opinions, findings, and conclusions or recommendations expressed in this material are those of the authors and do not necessarily reflect the views of the S.D. Bechtel, Jr. Foundation or the National Science